

## ABSTRACT OF THE DISCLOSURE

An acrylic derived adhesive that is used for attachment of a polarizing plate having a difference of no more than 5 % between an initial gel ratio and a gel ratio after the adhesive is heated at 80°C for 500 hours is efficiently used as adhesive for polarizing plate excellent in long-term preservation quality and for optical member.